



# TRANSFER & WASH CONDITIONS

## STANDARD PRODUCTS

## PRINTABLES PRODUCTS

		POLI-FLEX® PREMIUM	POLI-FLEX® BLOCKOUT SOFT	POLI-FLEX® NYLON	POLI-FLEX® STRETCH	POLI-FLEX® SPORT	POLI-FLEX® TURBO	TUBITHERM	TUBITHERM NEON COLOURS	POLI-FLEX® 5001 BLOCKOUT WHITE	POLI-FLEX® IMAGE REFLEX SILVER 4781 / REFLEX ECO 4782	POLI-FLEX® 4214 / 4215 DIMENSION	POLI-FLEX® IMAGE BRILLANT 421 / 431	POLI-FLEX® IMAGE LUMINOUS	POLI-FLEX® PEARL GLITTER	POLI-FLEX® IMAGE PAINT / GLOSSY	POLI-FLEX® IMAGE / STARFLEX	POLI-FLEX® IMAGE 4222 - 4275	TURBO PRINT 4036 MATT	ULTIMATE PRINT SOFT 4030/4032 MATT/4031 GLOSS	ULTIMATE PRINT MATT 4025	ULTIMATE PRINT SUPERSOFT 4033 MATT	TURBO PRINT TRANSPARENT SOFT 4034 MATT	POLI-FLEX® 4010-S BLOCKOUT	POLI-FLEX® 4015 / 4016	POLI-FLEX® 4600 / 4605	POLI-FLEX® 4655	POLI-FLEX® 4625	POLI-FLEX® 4665 METALLIC	SUBLI-FLOCK® 4675	SOLVENT-FLOCK 5901 / TUBITHERM PES	SOLVENT-FLOCK 5905				
TRANSFER CONDITIONS	Temperature (°C)	160	130	150	160	130	Standard 160 Nylon* 150 150 130	160	160	160	160	160	160	160	160	160	160	160	160	Standard 160 Nylon* 150 150 130	160	160	160	160	150	130	160	160	160	160	160	160	160	160	160	
	Pressure (bar)	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,0	2,0	2,0	2,5 3,0	2	3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0			
	Time (sec.)	15	5	Pre-pressing 4 Second pressing 10	15	10	3 4 5	5 5 10*	15	15	15	15	Pre-pressing 4 Second pressing 10	25	15	15	15	15	15	15	15	3 4 5	5 5 10*	15	15	15	15	Pre-pressing 4 Second pressing 10	5	15	15	15	15	15	15	15
	Peel (Warm= W / Cold= C)	W	W	W	W	W	W & C	W & C	W	C	W	W	W	C	C	C	C	W	W	W	C	W	W	W	W	C	W	W	W	W	W	W	W	W		
WASH CONDITIONS	Wash resistance (°C)	80	60	40	80	40	60	40	60	40	40	60	40	60	60	60	40	60	60	60	40	80	60	40	40	40	60	40	60	60	60	40	90	60	40	
	Tumble dry	●			●	●	●**		●	●		●		●	●	●	●	●	●	●	●	●			●	●	●	●	●	●	●	●	●	●	●	
	Dry cleaning	●	●		●	●	●																													

\*POLI-FLEX® TURBO & TURBO PRINT  
 • Pre-pressing 5 sec.  
 • Pressing on Nylon 5 sec.  
 • After Removing PET Liner 10 sec.

\*\* POLI-FLEX® TURBO TURBO PRINT  
 commercial tumble dryer up to 100°C